

JAC SHEETS

JAC SERILUX PLUS

Print carrier

JAC® SERILUX PLUS is a flexible PVC film for UV- and conventional offset printing. The film is used for the production of high-quality labels for indoor and outdoor application.

JAC® SERILUX PLUS displays a high degree of tear resistance and tear propagation resistance. They also display relatively good ageing stability, water resistance and lightfastness, depending on the actual applications for which they are used. For technical guidance please see our web side under “5.5 Application of JAC® films”

JAC® SERILUX PLUS as mentioned is suitable for conventional offset printing but with purely oxidative drying inks which are resistant to plasticiser and suitable for films. Consult your printing ink supplier about suitable printing inks for your particular application. For more details regarding Offset printing on films please see our website “5.6 Printing of JAC® films in Offset”. For printing with translucent inks please also see our technical documentation on our website.

The following print carriers are available ex. stock:

JAC® SERILUX 70090 – crystal clear, gloss

JAC® SERILUX 72090 – white, gloss

approx. RAL 9016.

Average values

Type N°	70090	72090
Weight (g/m ²)	104	122
Thickness (µm)	90	90
Tensile strength longitudinal (kN/m)	23	29
Wearing conditions ¹⁾ (years)	2	2

¹⁾ Under normal climatic conditions as prevailing in Central Europe.

For information regarding EHS regulation, please visit our website under downloads “Guidelines for Use 5.12 Product Compliance JAC Offset”.

Adhesive

PERMANENT is a water-based permanent acrylic adhesive. It has been specially developed for flexible PVC films. PERMANENT is distinguished by its high transparency and UV stability.

Average values

	PERMANENT
Adhesion (N/25 mm) (FTM 1 on st. steel/20 min. bond time)	15.4
Tack (N) (FTM 9 on st. steel)	10.3
Recommended minimum application temperature (°C)	+5
Heat resistance (in °C)	+80
Resistance to cold (°C) ²⁾ down to	-20 Good
Shelf life of laminate (years) ⁵⁾	1

²⁾ Strength of adhesion may be adversely affected by a possible migration of plasticizer from the flexible PVC film into the adhesive.

³⁾ Not fully resistant until after adhesion reaches full strength - after at least 24 hrs

⁴⁾ If not exposed to direct sunlight; applied at room temperature

⁵⁾ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

Silicone paper

B120 is a silicized, special-purpose lightweight board, wood free, matt on reverse side, moisture-stabilized through specially impregnated fibres and special coating, hence its excellent flatness.

B120 SPLIT is as above, but with scored lines running in machine direction and spaced 6,25 cm apart serving as a peel off aid.

Average values

	B 120
Weight (g/m ²)	120
Thickness (µm)	118

Last updated July 2024

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

Fasson® and Crack-Back® are registered trademarks of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.