

JAC SHEETS

JAC DIGILABEL FILMS

Description of JAC® Digilabel Films for Indigo Sheets - These products have been specially developed for the use on HP Indigo Digital Printing Systems. The face material guarantees good toner adhesion. A 100% ink transfer from the blanket to the substrate significantly reduces cleaning requirements. The excellent ink bonding avoids damage when scratching. The superb flatness ensures good runnability, smooth passing through the machine and clean kiss-cutting. Make sure the surface is clean, dry and free of oil or grease before applying the label.

	Adhesive	Silicone paper	Measurement / Box Content
Digilabel PE White Matt	PERMANENT	B90	32 x 46 cm/175 sheets per box
Digilabel PET Clear Gloss	PERMANENT	B120	32 x 46 cm/250 sheets per box

Print carrier

Average values

Digilabel PE White Matt – single layer PE-Foil, white, matt.

Digilabel PET Clear Gloss – PET-Foil, transparent, glossy.

105 For print guidance please visit our website under Downloads “5.11 Storage\printing on Digilabel”.

For technical guidance please visit our website under downloads “Guidelines for use – Offset printing.

For information regarding EHS regulation, please visit our website under downloads “Guidelines for Use 5.12 Product Compliance JAC Offset”.

	PE White Matt	PET Clear Gloss
Weight (g/m ²)	115	105
Weight total laminate (g/m ²)	223	243
Thickness (µm)	178	75
Thickness total laminate (µm)	280	205
Tensile strength ISO 1924/2 (kN/m)	2.3	-
Gloss (60°)	-	-
Opacity (%)	92	-
Shelf life of laminate ¹⁾ (years)	2	2

¹⁾ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

Adhesive

Average values

PERMANENT is a crystal clear, acrylic-based adhesive with ma. UV- and weather resistance. Good initial and final adhesion. Resistant against high temperatures.

	PERMANENT
Adhesion (N/25 mm) (FTM 1 peel 180° 20'/stainless steel)	15.4
Tack (N) (FTM 9 on stainless steel)	10.3
Recommended minimum application temperature (°C)	+5
Heat resistance (in °C)	+80
Resistance to cold (°C) ²⁾ down to	-20
Ageing stability ³⁾	Very good

²⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

³⁾ If not exposed to direct sunlight.

⁴⁾ Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

Silicone paper

Average values

Silicone paper B90 – is a very stable, siliconized special-purpose paper which displays good flatness and die cutting properties.

B120 – is a siliconized, special-purpose lightweight board, which displays high dimensional stability.

	B 90	B120
Weight (g/m ²)	90	120
Thickness (µm)	90	118

Last updated July 2025

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms> Fasson® and Crack-Back® are registered trademarks of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.